



VpCI®-337 / GE / Winterized



VpCI®-337 GE is specially formulated to be used in systems that are sensitive to sodium and sulfur.

**Please review your application with Cortec® Technical Service prior to commissioning.*

FEATURES

- Biodegradable (87% biodegradation in 28 days)*
- Contains vapor and contact corrosion inhibitors which provide multi-metal corrosion protection
- Leaves a thin, self-healing film
- Ready-to-use
- Protection is immediate, convenient to apply, and easy to remove if required

*Biodegradability applies to VpCI®-337 only

PRODUCT DESCRIPTION

VpCI®-337 is a ready-to-use waterborne corrosion inhibitor used primarily for robust preservation of internal void spaces. Vapor phase Corrosion Inhibitors (VpCI®) in VpCI®-337 migrate to protect metal surfaces resulting in time and cost savings. When combined with labor-saving techniques, minimum amount of product can be used to protect large areas or volumes. VpCI-337 is effective on multiple metals.

VpCI®-337 is a combination of contact and vapor corrosion inhibitors, which allows a wide range of uses; from low-dose void-space protection to steel coil edge spray.

Pipes, tanks, and other equipment protected by VpCI®-337 are ready-for-use or commissioning, often without the need for removal*. VpCI®-337 is completely water-soluble allowing ease of use for pigging, purging, or other existing processes. No degreasing or stripping is necessary. The metal will retain a clean and rust-free surface. In most cases, the thin protective film will not affect paint processes, conductivity, appearance, or any other important property of metals or alloys.

VpCI®-337 Winterized has a lower freezing point for the convenience of application and storage in cold temperatures.

TYPICAL APPLICATION

- Pipe, spool, modules
- Void space protection
- Edge spray for coils
- Double wall spaces
- Complex internal cavities
- Deep storage of key assets

METALS PROTECTED

- Hot/cold-rolled steel
- Silicon steel
- Stainless steel
- Cast iron
- Zinc
- Aluminum
- Copper
- Brass

TYPICAL PROPERTIES

VpCI®-337/VpCI®-337 GE

Appearance	Clear to hazy amber liquid
Carrier	Water
Film Type	Thin, soft film
Flash Point	>200 °F (93 °C)
Freeze Point	32 °F (0 °C)
pH	7.2-9.0 (neat)
Weight per Gallon	8.7-8.9 lb/gal (1.04-1.06 kg/l)

VpCI®-337 Winterized

Appearance	Clear amber liquid
Carrier	Water + Propylene Glycol
Freeze Point	-47.2 °F (-44 °C)
pH	7.0-8.6 (neat)
Weight per Gallon	8.8-9.2 lb/gal (1.05-1.10 kg/l)

Note: Product may become hazy after a few days.

APPLICATION

Mix thoroughly prior to application.

Fog or mist into containers, boxes, crates, and shrouded packages at a rate of 0.5-1.0 oz./ft³ (0.5-1.0 L/m³) of enclosed space. Always spray VpCI®-337 uniformly within enclosure and allow direct access of vapors to metal surfaces to be protected.

Please contact Cortec® Technical Service for specific dosing and equipment recommendations, and for application guidance.

PACKAGING AND STORAGE

VpCI®-337 and VpCI®-337 GE are packaged in 5 gallon (19 liter) plastic pails, 55 gallon (208 liter) metal drums, totes, and bulk.

Minimum storage temperature: 40 °F (4 °C)

Maximum storage temperature: 120 °F (49 °C)

VpCI®-337 Winterized is packaged in 5 gallon (19 liter) plastic pails, 55 gallon (208 liter) metal drums, totes, and bulk.

Minimum storage temperature: -40 °F (-40 °C)

Maximum storage temperature: 120 °F (49 °C)

Shelf life: 24 Months

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.
BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
www.cortecvci.com

Printed on recycled paper  100% post consumer

Revised: 07/26/19. Supersedes: 07/25/18. ©Cortec Corporation 2002-2018 of Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2018, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by: